



Sintergewebe	Bezeichnung	Geometrische Porengrösse μm	Dicke mm	Porösität %	Druckverlust mbar	As mm^2 / cm	Rp N / cm	Gewicht kg / m^2	spez. Durchfluss-Kennzahl Eu
Poreflo	PF-303		1.25	10	100	5.2	1101	8.8	75683
	PF-304		1.45	15	50	5.2	1101	9.6	37841
	PF-305		1.6	20	20	5.2	1101	9.9	15137
	PF-206		0.85	10	10	4.8	1016	7.2	7568
	PF-207		1	12	5	4.8	1016	7.2	3784
	PF-208		1.05	14	2.5	4.8	1016	7.3	1892
	PF-209		1.2	20	1.25	4.8	1016	7.5	946
	PF-211		1.45	35	0.7	4.8	1016	7.5	530

Version: 01.05.2015